


55STC3663454N40

06.05.2011 - Rev. 4

STAIR TREAD COVER

| | |
|------------------|--|
| Thickness | mm 4 |
| Color | Grey RAL 7004 (yellow front plate) <i>indicative RAL reference</i> |

| | |
|----------------------|---|
| Raw materials | Polyester Resin |
| | Roving glass fiber + Mat and Woven Fabric type "E" |
| | Inorganic fillers without halogens |

| | | | | |
|--|---|------------------|-------------------------|--|
| Standard pieces |  | | | |
| mm 345 x 3660 | | | | |
| height mm 40 | | | | |
| | | | | |
| weight kg/m ² 2 | | | | |
| <table border="1"> <tr> <td>tolerance</td> <td>± mm 5 piece dimensions</td> </tr> <tr> <td></td> <td>± mm 2 thickness</td> </tr> </table> | | tolerance | ± mm 5 piece dimensions | |
| tolerance | ± mm 5 piece dimensions | | | |
| | ± mm 2 thickness | | | |

| | | | |
|----------------|---|--------|---------------------------------------|
| Surface | A | quartz | Antiskid level R13 V4 norm DIN E51130 |
|----------------|---|--------|---------------------------------------|

| | | |
|-------------------------|-----------------------|---|
| Reaction to fire | Fire retardant | Spread ≤ 25 norm ASTM E84-98 |
| | | Level V-0 norm UL94 Vertical Burning Test |

| | |
|--------------------------|--|
| Ageing resistance | Ageing test made with UV lamp according to ASTM G154-06 and passed with 5 points on the gray range and without evident defects (test made with 1500 hours of exposure to 4 hours alternate cycles at a UV temperature of 60°C and 4 hours at a condensed temperature of 50°C irradiated by UVB 313 nm lamp, radiance 0,71 W/m ²) |
| | After the exposure to heat, cold and humidity cycles according to UNI EN ISO 9142/04 norm (n° 21 cycles type D3) there is no evidence of defects |