

Channel coverings, inside width mm 500 Grating type SCH 38/25C_IFR

Document: VC05-SCH38/25C REV. 00	
Grating type: SCH38/25C	
	LOAD 1000 daN - channel open span mm 500
28	
Material:	FRP – made with polyester resin reinforced with continuous glass fibers
	placed in both directions in equal percentage. Direct roving glass fiber
	type "E", mat and lath. Inorganic fillers without halogens.
Mesh:	mm 38x38
Beam height:	mm 25
Beam thickness:	mm 5-7
Cover plate:	cover with mm 3 thickness plates
Total height:	mm 28 (25+3)
Color:	Gray RAL 7004 – mass colored and varnished with polyurethane paint
Surface finishing:	antiskid finishing on one plate made with quartz level R13V4 according to DIN 51130 norm
Distance between supports	mm 500
(inside channel dimensions)	
Deflection break download	>6000/7000 daN
with center line load:	
Mechanical and durability	-DIN 24537-3: Gratings used as floor covering – part 3
characteristics determined and	-EN 1990:2004/A1:2006: Eurocode – basis of structural design
tested according to the norms:	, and the second
Reaction to fire:	SELF ESTINGUISHING according to:
	norm EN 13501-1_2007 level B _{fl} – s1
	norm ASTM E84-98 spread ≤ 25
	norm AFNOR NFP 92-501 level M2
	norm DIN 4102 -14 level B2
Resistivity and RS surface and	norm EN 61340-2.3 par. 8.1 e 8.2 ref. to ISO 1853, IEC 60167, HD 568
Rt transversal electric	S1 – excellent insulator according to the safety norms
resistance:	150 04040 4 5 051 04 4/0/0 0 0 40 5 150 00405 1/5 500 04
Resistivity and safety electric	norm IEC 61340-4-5- CEI 64-4/8/6 par. 6.12.5 – IEC 60167 – HD 568 S1:
resistance to ground human	excellent insulator according to the safety norms
body model	ACTM D 440 07
Dielectric strength with rated	norm ASTM D 149-97a: very low current absorption, according to the safety
voltage:	norms
Ageing resistance:	Ageing test made with UV lamp according to ASTM G154-06 and passed
Evnouve toot to heat sold and	with 5 points on the gray range and without evident defects
Exposure test to heat, cold and	According to UNI EN ISO 9142/04 norm (n.21 cycles type D3) passed
humidity cycles:	without evident defects.



M.M. S.r.l.

Via A. Zanussi 300 / 302, 33100 Udine (Italy)
Ph. +39 0432.602218 / 522970 - Fax. +39 0432.522253
info@mmgrigliati.it - www.mmgrigliati.it

VC05 SCH38/25C

27.02.2012 Rev. 0 AZIENDA CON SISTEMA DI GESTIONE PER LA QUALITÀ CERTIFICATO DA DNV = UNI EN ISO 9001:2008 =