

M.M. S.R.L. Fiberglass Reinforced Polymer gratings and structures

Via Antonio Zanussi, 300/302 33100 Udine - Italy Cap. Soc. EURO 100.000 i.v. P.lva / C.F. 00477620306 Reg. Imp. UD 00477620306 R.E.A. UD-138461 ph. +39.0432.522970 fax +39.0432.522253 info@mmgrigliati.it




SCH 38/17C_IFR

ESD line

06.05.2011 - Rev. 4

| Mesh | mm | 38 > | x 38 |
|-----------------|----------------|------|-------------|
| Thickness | mm | 20 | |
| Cover thickness | mm | 3 | |
| Bearing bar | mm | 7 | upper part |
| thickness | mm | 5 | bottom part |
| Color | Top Coat Black | | |

MOLDED GRATINGS



| Raw materials | Polyester Resin | |
|---------------|---|--|
| | Roving glass fiber + Mat and Woven Fabric type"E" | |
| | Inorganic fillers without halogens | |

| Resin type | Modulus of elasticity | Ultimate stress |
|------------|-----------------------|-----------------|
| IFR | 15000 MPa | 250 MPa |

| Stand | lard panels | |
|-----------|---------------|------------|
| mm | 1220 x 3660 | EFRIC SID |
| | | BERNE SIDE |
| | | |
| | | |
| | | |
| Weigl | ht kg/m² 15 | |
| | ± mm 5 panel | |
| tolerance | dimensions | |
| | ± mm 2 height | |

| IFR-ESD line | Top Coat Polyester with Carbon black conductive powder | | |
|--|--|---|--|
| Surface | A Quartz | Antiskid level R13 V4 norm DIN 51130 | |
| Departies to fire | Fire retardant | Spread ≤ 25 norm ASTM E84-98 | |
| Reaction to fire | rirë retardant | ASTM D635 Elapsed time and burned length < 25 mm | |
| Surface and Volume electrical resistivity. Dielectric strength | Antistatic Dissipative | EN 61340-2.3 Par. 8.1 and 8.2 – IEC 61340-4.1 Par. 5.1.2 ref. ISO 1957 – IEC 61340-4.5 – ASTM D149-97a | |



Via Antonio Zanussi, 300/302 33100 Udine - Italy Cap. Soc. EURO 100.000 i.v. P.lva / C.F. 00477620306 Reg. Imp. UD 00477620306 R.E.A. UD-138461 ph. +39.0432.522970 fax +39.0432.522253 info@mmgrigliati.it



LOADS

MAXIMUM SUGGESTED LOADS

| Type of support | On the line of the two ends of the panel |
|----------------------|--|
| | |
| Limits determined by | Deflection (load sagging) |
| | |

the maximum deflection admitted, is 1/200 of the distance between the supports

According to the standard DIN 24537-3 deviation due to the load may be no more than 1/200 of the land width and the difference in height between neighbouring joints between loaded and unloaded floor coverings may be no more than 4 mm.

| DISTRIBUTED LOAD | A CONTRACTOR OF A CONTRACTOR O | |
|---------------------|--|------------------|
| | | T |
| Distance between | Load with | Load with |
| supports | deflection equal | deflection equal |
| | to 1/200 | to 1/100 |
| [cm] | [kg/m ²] | |
| 30 | 4550 | 9100 |
| 50 | 950 | 1950 |
| 70 | 350 | 700 |
| 90 | 150 | 300 |
| | | |

Limits determined by

| CONCENTRATED LOAD | | |
|---------------------------|---|---|
| Distance between supports | Load with deflection equal to 1/200 | Load with deflection equal to 1/100 |
| [cm] | 10 1/200 [a | |
| 30 | 850 | 1700 |
| 50 | 300 | 600 |
| 70 | 150 | 300 |
| 90 | 50 | 150 |

All lighter loads are admitted

Admitted stresses (stress determined by the load)

the **maximum admitted stress** is 1/5 of the ultimate stress (safety factor is equal to 0.20 – the ultimate stress is 5 times the specified load)

| DISTRIBUTED LOAD | and the second sec | CONCENTRATED LOAD | |
|---------------------------|--|------------------------------|-----------------------|
| Distance between supports | Maximum admitted load | Distance between supports | Maximum admitted load |
| [cm] | [kg/m²] | [cm] | [kg/m] |
| 30 | 6850 | 30 | 1000 |
| 50 | 2450 | 50 | 600 |
| 70 | 1250 | 70 | 400 |
| 90 | 750 | 90 | 300 |

All lighter loads are admitted

- The above characteristics are meant as reference values for standard material in ambient working temperature. Even if they are not to be considered as guaranteed characteristics they are based on our experience and are supplied in good faith.

According to the standard DIN 24537-3 the conversion safety factor should be 0.75 for internal environmental exposure conditions, 0.65 for external exposure conditions, and 0.50 for aggressive exposure conditions.

- No matter which are the exposure conditions, chemical resistance must be always verified by contacting M.M. technical department.

- In case of heavy duty load compressive strength must be verified.