

Via Antonio Zanussi, 300/302 33100 Udine - Italy Cap. Soc. EURO 100.000 i.v. P.Iva / C.F. 00477620306 Reg. Imp. UD 00477620306 R.E.A. UD-138461 ph. +39.0432.522970 fax +39.0432.522253 info@mmgrigliati.it




SCH 38/30C_IFR

06.05.2011 - Rev. 4

MOLDED GRATINGS

Mesh	mm	38 >	c 38
Thickness	mm	33	
Cover thickness	mm	3	
Bearing bar thickness	mm	7	upper part
	mm	5	bottom part
Color	Grey		7004 ive RAL reference



	Polyester Resin
Raw materials	Roving glass fiber + Mat and Woven Fabric type"E"
	Inorganic fillers without halogens

Resin type	Modulus of elasticity	Ultimate stress
IFR	15000 MPa	250 MPa

Stand	lard panels	
mm	1000 x 2000	BEARING SID
mm	1000 x 4038	BEARING SIDE
mm	1220 x 3660	
Weigh	t kg/m² 23	
tolerance	± mm 5 panel dimensions	
	± mm 2 height	

Surface	А	Quartz	Antiskid level R13 V4 norm DIN 51130		
Decetion to fine		Pina mata mila mat	Spread ≤ 25 norm ASTM E84-98		
Reaction to fire	Fire retardant		Level B _{fl} -S1 norm EN 13501-1		
Ageing test made with UV lamp according to ASTM G154-06 and passed with 5 points of gray range and without evident defects (test made with 1500 hours of exposure to 4 hours alternate cycles at a UV temperature of 60°C and 4 hours at a condensed temperature of 50 irradiated by UVB 313 nm lamp, radiance 0,71 W/m²)		defects (test made with 1500 hours of exposure to 4 hours of 60°C and 4 hours at a condensed temperature of 50°C			
	After the exposure to heat, cold and humidity cycles according to UNI EN ISO 9142/04 norm (n° 21 cycles type D3) there is no evidence of defects				



M.M. S.R.L.
Fiberglass Reinforced Polymer
gratings and structures

Via Antonio Zanussi, 300/302 33100 Udine - Italy Cap. Soc. EURO 100.000 i.v. P.Iva / C.F. 00477620306 Reg. Imp. UD 00477620306 R.E.A. UD-138461 ph. +39.0432.522970 fax +39.0432.522253 info@mmgrigliati.it



LOADS

MAXIMUM SUGGESTED LOADS

	Type of support	On the line of the two ends of the panel
--	-----------------	--

Limits determined by **Deflection** (load sagging)

the maximum deflection admitted, is 1/200 of the distance between the supports

According to the standard DIN 24537-3 deviation due to the load may be no more than 1/200 of the land width and the difference in height between neighbouring joints between loaded and unloaded floor coverings may be no more than 4 mm.

DISTRIBUTED LOAD			CONCENTRATED LOAD		
Distance between	Load with	Load with	Distance between	Load with	Load with
supports	deflection equal	deflection equal	supports	deflection equal	deflection equal
	to 1/200	to 1/100		to 1/200	to 1/100
[cm]	[kg/m²]		[cm]	[cm]	
50	4050	8100	50	1250	2500
70	1450	2950	70	600	1250
90	650	1350	90	350	750
110	350	750	110	250	500

All lighter loads are admitted

Limits determined by Admitted stresses (stress determined by the load)

the **maximum admitted stress** is 1/5 of the ultimate stress (safety factor is equal to 0.20 – the ultimate stress is 5 times the specified load)

DISTRIBUTED LOAD		CONCENTRATED LOAD	
Distance between supports	Maximum admitted load	Distance between supports	Maximum admitted load
[cm]	[kg/m²]	[cm]	[kg/m]
50	6550	50	1600
70	3350	70	1150
90	2000	90	900
110	1350	110	700

- The above characteristics are meant as reference values for standard material in ambient working temperature. Even if they are not to be considered as guaranteed characteristics they are based on our experience and are supplied in good faith.
- According to the standard DIN 24537-3 the conversion safety factor should be 0.75 for internal environmental exposure conditions, 0.65 for external exposure conditions, and 0.50 for aggressive exposure conditions.
- No matter which are the exposure conditions, chemical resistance must be always verified by contacting M.M. technical department.
- In case of heavy duty load compressive strength must be verified.