


SCH 40/38C_ISO


06.05.2011 - Rev. 4

MOLDED GRATINGS

Mesh	mm 40 x 40	
Thickness	mm 45	
Cover thickness	mm 5	
Bearing bar thickness	mm 8 upper part	
	mm 7 bottom part	
Color	Translucent green	

Raw materials	ISOPHTHALIC Polyester Resin	
	Roving glass fiber + Mat and Woven Fabric type "E"	
	Without inorganic fillers	

Resin type	Modulus of elasticity	Ultimate stress
ISO	12250 MPa	250 MPa

Standard panels	
mm 1000 x 2000	
mm 1200 x 3000	
Weight kg/m² 27	
tolerance	
± mm 5 panel dimensions	
± mm 2 height	



Surface	A	Quartz	Antiskid level R13 V4 norm DIN 51130
----------------	---	---------------	---

Ageing resistance	Ageing test made with UV lamp according to ASTM G154-06 and passed with 5 points on the gray range and without evident defects (test made with 1500 hours of exposure to 4 hours alternate cycles at a UV temperature of 60°C and 4 hours at a condensed temperature of 50°C irradiated by UVB 313 nm lamp, radiance 0,71 W/m ²)
	After the exposure to heat, cold and humidity cycles according to UNI EN ISO 9142/04 norm (n° 21 cycles type D3) there is no evidence of defects

LOADS



MAXIMUM SUGGESTED LOADS

Type of support	On the line of the two ends of the panel
Limits determined by	Deflection (load sagging)
the maximum deflection admitted , is 1/200 of the distance between the supports	
According to the standard DIN 24537-3 deviation due to the load may be no more than 1/200 of the land width and the difference in height between neighbouring joints between loaded and unloaded floor coverings may be no more than 4 mm.	

DISTRIBUTED LOAD			CONCENTRATED LOAD		
	Distance between supports [cm]	Load with deflection equal to 1/200 [kg/m ²]		Distance between supports [cm]	Load with deflection equal to 1/200 [cm]
		Load with deflection equal to 1/100			Load with deflection equal to 1/100
50	9850	19750	50	3050	6150
70	3600	7200	70	1550	3150
90	1650	3350	90	950	1900
110	900	1850	110	600	1250

All lighter loads are admitted

Limits determined by	Admitted stresses (stress determined by the load)
the maximum admitted stress is 1/5 of the ultimate stress (safety factor is equal to 0.20 – the ultimate stress is 5 times the specified load)	

DISTRIBUTED LOAD			CONCENTRATED LOAD		
	Distance between supports [cm]	Maximum admitted load [kg/m ²]		Distance between supports [cm]	Maximum admitted load [kg/m]
50	14500		50	3600	
70	7400		70	2550	
90	4450		90	2000	
110	2950		110	1600	

All lighter loads are admitted

- The above characteristics are meant as reference values for standard material in ambient working temperature. Even if they are not to be considered as guaranteed characteristics they are based on our experience and are supplied in good faith.
- According to the standard DIN 24537-3 the conversion safety factor should be 0.75 for internal environmental exposure conditions, 0.65 for external exposure conditions, and 0.50 for aggressive exposure conditions.
- No matter which are the exposure conditions, chemical resistance must be always verified by contacting M.M.technical department.
- In case of heavy duty load compressive strength must be verified.