

M.M. S.R.L. Fiberglass Reinforced Polymer gratings and structures


Via Antonio Zanussi, 300/302 33100 Udine - Italy Cap. Soc. EURO 100.000 i.v. P.lva / C.F. 00477620306 Reg. Imp. UD 00477620306 R.E.A. UD-138461 ph. +39.0432.522970 fax +39.0432.522253 info@mmgrigliati.it



SCH 52/100C_CFR 06.05.2011 - Rev. 4


MOLDED GRATINGS

Mesh	mm 52 x 52 main
mean	mm 26 x 26 secondary
Thickness	mm 103
Cover thickness	mm 3
Bearing bar	mm 10 upper part
thickness	mm 8 bottom part
Color	Black



	Polyester Resin
Raw materials	Roving glass fiber + Mat and Woven Fabric type"E"
	Inorganic fillers without halogens + Carbon black conductive powder

Resin type	Modulus of elasticity	Ultimate stress
CFR	15000 MPa	250 MPa



Surface	A	Quartz		Antiskid level R13 V4 norm DIN 51130	
Reaction to fire	Fire retardant			Spread ≤ 25 norm ASTM E84-98	
Reaction to me	Fire felaruant		ASTM D635 Elapsed time and burned length < 25 mm		
Surface and Volume electrical resistivity. Dielectric strength	Exc	ellent Conductivity	EN 61340-2.3 Par. 8.1 and 8.2 – IEC 61340-4.1 Par. 5.1.2 ref. ISO 1957 – IEC 61340-4.5 - ASTM D149-97a		



Via Antonio Zanussi, 300/302 33100 Udine - Italy Cap. Soc. EURO 100.000 i.v. P.lva / C.F. 00477620306 Reg. Imp. UD 00477620306 R.E.A. UD-138461 ph. +39.0432.522970 fax +39.0432.522253 info@mmgrigliati.it



LOADS

MAXIMUM SUGGESTED LOADS

Type of support	On the line of the two ends of the panel
Limits determined by	Deflection (load sagging)

the **maximum deflection admitted**, is 1/200 of the distance between the supports According to the standard DIN 24537-3 deviation due to the load may be no more than 1/200 of the land width and the difference in height between neighbouring joints between loaded and unloaded floor coverings may be no more than 4 mm.

DISTRIBUTED LOAD	and the second s	
Distance between	Load with	Load with
supports	deflection equal	deflection equal
	to 1/200	to 1/100
[cm]	[kg	/m²]
80	24800	49600
100	12700	25400
120	7350	14700
140	4600	9250

Limits determined by

CONCENTRATED LOAD		
Distance between	Load with	Load with
supports	deflection equal	deflection equal
	to 1/200	to 1/100
[cm]	[cm]	
80	12400	24800
100	7900	15850
120	5500	11000
140	4050	8100

All lighter loads are admitted

Admitted stresses (stress determined by the load)

the **maximum admitted stress** is 1/5 of the ultimate stress (safety factor is equal to 0.20 – the ultimate stress is 5 times the specified load)

DISTRIBUTED LOAD	and the second s	CONCENTRATED LOAD	
Distance between supports	Maximum admitted load	Distance between supports	Maximum admitted load
[cm]	[kg/m ²]	[cm]	[kg/m]
80	23900	80	9550
100	15300	100	7650
120	10600	120	6350
140	7800	140	5450

All lighter loads are admitted

- The above characteristics are meant as reference values for standard material in ambient working temperature. Even if they are not to be considered as guaranteed characteristics they are based on our experience and are supplied in good faith.

According to the standard DIN 24537-3 the conversion safety factor should be 0.75 for internal environmental exposure conditions, 0.65 for external exposure conditions, and 0.50 for aggressive exposure conditions.

- No matter which are the exposure conditions, chemical resistance must be always verified by contacting M.M.technical department.

- In case of heavy duty load compressive strength must be verified.