

Via Antonio Zanussi, 300/302 33100 Udine - Italy Cap. Soc. EURO 100.000 i.v. P.Iva / C.F. 00477620306 Reg. Imp. UD 00477620306 R.E.A. UD-138461 ph. +39.0432.522970 fax +39.0432.522253 info@mmgrigliati.it




## SCH 52/52C\_IFR

06.05.2011 - Rev. 4

# **MOLDED GRATINGS**

Mesh	<b>mm</b> 52 x 52 main		
Wiesii	mm 26 x 26 secondary		
Thickness	mm 55		
Cover thickness	mm 3		
Bearing bar	mm 8 upper part		
thickness	mm 7 bottom part		
Color	Grey RAL 7004 indicative RAL reference		



	Polyester Resin
Raw materials	Roving glass fiber + Mat and Woven Fabric type"E"
	Inorganic fillers without halogens

Resin type	Modulus of elasticity	Ultimate stress
IFR	15000 MPa	250 MPa

Standard panels	<i>★ 7</i> .
mm 1000 x 3000	Store Store
mm 1000 x 4050	
Weight kg/m <sup>2</sup> 35,5	
tolerance ± mm 5 panel dimensions ± mm 2 height	

Surface	Α	Quartz		Antiskid level R13 V4 norm DIN 51130	
Decetion to fine	Spread ≤ 25 norm ASTM E84-98				
Reaction to fire	Fire retardant		Level B <sub>ff</sub> -S1 norm EN 13501-1		
Ageing resistance	Ageing test made with UV lamp according to ASTM G154-06 and passed with 5 points on the gray range and without evident defects (test made with 1500 hours of exposure to 4 hours alternate cycles at a UV temperature of 60°C and 4 hours at a condensed temperature of 50°C irradiated by UVB 313 nm lamp, radiance 0,71 W/m²)  After the exposure to heat, cold and humidity cycles according to UNI EN ISO 9142/04 norm (n° 21 cycles type D3) there is no evidence of defects				



M.M. S.R.L. Fiberglass Reinforced Polymer gratings and structures

Via Antonio Zanussi, 300/302 33100 Udine - Italy Cap. Soc. EURO 100.000 i.v. P.Iva / C.F. 00477620306 Reg. Imp. UD 00477620306 R.E.A. UD-138461 ph. +39.0432.522970 fax +39.0432.522253 info@mmgrigliati.it



### **LOADS**

#### MAXIMUM SUGGESTED LOADS

	Type of support	On the line of the two ends of the panel
--	-----------------	--

Limits determined by **Deflection** (load sagging)

the maximum deflection admitted, is 1/200 of the distance between the supports

According to the standard DIN 24537-3 deviation due to the load may be no more than 1/200 of the land width and the difference in height between neighbouring joints between loaded and unloaded floor coverings may be no more than 4 mm.

DISTRIBUTED LOAD			CONCENTRATED LOAD		
Distance between	Load with	Load with	Distance between	Load with	Load with
supports	deflection equal	deflection equal	supports	deflection equal	deflection equal
	to 1/200	to 1/100		to 1/200	to 1/100
[cm]	[kg/m²]		[cm]	[c	m]
70	5750	11550	70	2500	5050
90	2700	5400	90	1500	3050
110	1450	2950	110	1000	2000
130	900	1800	130	700	1450

## All lighter loads are admitted

## Limits determined by Admitted stresses (stress determined by the load)

the **maximum admitted stress** is 1/5 of the ultimate stress

(safety factor is equal to 0.20 - the ultimate stress is 5 times the specified load)

DISTRIBUTED LOAD		CONCENTRATED LOAD	
Distance between supports	Maximum admitted load	Distance between supports	Maximum admitted load
[cm]	[kg/m²]	[cm]	[kg/m]
70	8300	70	2900
90	5000	90	2250
110	3350	110	1850
130	2400	130	1550

- The above characteristics are meant as reference values for standard material in ambient working temperature. Even if they are not to be considered as guaranteed characteristics they are based on our experience and are supplied in good faith.
- According to the standard DIN 24537-3 the conversion safety factor should be 0.75 for internal environmental exposure conditions, 0.65 for external exposure conditions, and 0.50 for aggressive exposure conditions.
- No matter which are the exposure conditions, chemical resistance must be always verified by contacting M.M.technical department.
- In case of heavy duty load compressive strength must be verified.