

Via Antonio Zanussi, 300/302 33100 Udine - Italy Cap. Soc. EURO 100.000 i.v. P.Iva / C.F. 00477620306 Reg. Imp. UD 00477620306 R.E.A. UD-138461 ph. +39.0432.522970 fax +39.0432.522253 info@mmgrigliati.it




SCH 52/52C_CFR

06.05.2011 - Rev. 4

MOLDED GRATINGS

| Mesh | mm 52 x 52 main | | |
|-----------------|------------------------|--|--|
| Wesii | mm 26 x 26 secondary | | |
| Thickness | mm 55 | | |
| Cover thickness | mm 3 | | |
| Bearing bar | mm 8 upper part | | |
| thickness | mm 7 bottom part | | |
| Color | Black | | |
| | · | | |
| | | | |



| | Polyester Resin |
|---------------|---|
| Raw materials | Roving glass fiber + Mat and Woven Fabric type"E" |
| | Inorganic fillers without halogens + Carbon black conductive powder |

| | Resin type | Modulus of elasticity | Ultimate stress |
|----------------------|------------|-----------------------|-----------------|
| CFR 15000 MPa | | 15000 MPa | 250 MPa |

| Standa | rd panels | & 7 . |
|-----------|----------------------------|-------------|
| mm 10 | 000 x 3000 | Store Store |
| mm 10 | 000 x 4050 | Sup. |
| | | |
| | | |
| Weight | kg/m² 35,5 | |
| tolerance | ± mm 5 panel dimensions | |
| | ± mm 2 height | |

| Surface | Α | Quartz | | Antiskid level R13 V4 norm DIN 51130 | |
|--|--------------------|---------------------|--|---|--|
| December to fine | ire Fire retardant | | Spread ≤ 25 norm ASTM E84-98 | | |
| Reaction to fire | | | ASTM D635 Elapsed time and burned length < 25 mm | | |
| Surface and Volume electrical resistivity. Dielectric strength | Exc | ellent Conductivity | EN 613 | 40-2.3 Par. 8.1 and 8.2 – IEC 61340-4.1 Par. 5.1.2 ref. ISO 1957 – IEC 61340-4.5 - ASTM D149-97a | |



M.M. S.R.L. Fiberglass Reinforced Polymer gratings and structures

Via Antonio Zanussi, 300/302 33100 Udine - Italy Cap. Soc. EURO 100.000 i.v. P.Iva / C.F. 00477620306 Reg. Imp. UD 00477620306 R.E.A. UD-138461 ph. +39.0432.522970 fax +39.0432.522253 info@mmgrigliati.it



LOADS

MAXIMUM SUGGESTED LOADS

| Type of support | On the line of the two ends of the panel |
|-----------------|--|
| | |

Limits determined by **Deflection** (load sagging)

the maximum deflection admitted, is 1/200 of the distance between the supports

According to the standard DIN 24537-3 deviation due to the load may be no more than 1/200 of the land width and the difference in height between neighbouring joints between loaded and unloaded floor coverings may be no more than 4 mm.

| DISTRIBUTED LOAD | | | CONCENTRATED LOAD | | |
|---------------------------|-------------------------------------|-------------------------------------|---------------------------|-------------------------------------|-------------------------------------|
| Distance between supports | Load with deflection equal to 1/200 | Load with deflection equal to 1/100 | Distance between supports | Load with deflection equal to 1/200 | Load with deflection equal to 1/100 |
| [cm] | [kg/m²] | | [cm] | [kg/m] | |
| 70 | 5750 | 11550 | 70 | 2500 | 5050 |
| 90 | 2700 | 5400 | 90 | 1500 | 3050 |
| 110 | 1450 | 2950 | 110 | 1000 | 2000 |
| 130 | 900 | 1800 | 130 | 700 | 1450 |

All lighter loads are admitted

Limits determined by Admitted stresses (stress determined by the load)

the **maximum admitted stress** is 1/5 of the ultimate stress (safety factor is equal to 0.20 – the ultimate stress is 5 times the specified load)

| DISTRIBUTED LOAD | | CONCENTRATED LOAD | | |
|---------------------------|-----------------------|---------------------------|-----------------------|--|
| Distance between supports | Maximum admitted load | Distance between supports | Maximum admitted load | |
| [cm] | [kg/m²] | [cm] | [kg/m] | |
| 70 | 8300 | 70 | 2900 | |
| 90 | 5000 | 90 | 2250 | |
| 110 | 3350 | 110 | 1850 | |
| 130 | 2400 | 130 | 1550 | |

- The above characteristics are meant as reference values for standard material in ambient working temperature. Even if they are not to be considered as guaranteed characteristics they are based on our experience and are supplied in good faith.
- According to the standard DIN 24537-3 the conversion safety factor should be 0.75 for internal environmental exposure conditions, 0.65 for external exposure conditions, and 0.50 for aggressive exposure conditions.
- No matter which are the exposure conditions, chemical resistance must be always verified by contacting M.M.technical department.
- In case of heavy duty load compressive strength must be verified.