

Via Antonio Zanussi, 300/302 33100 Udine - Italy Cap. Soc. EURO 100.000 i.v. P.lva / C.F. 00477620306 Reg. Imp. UD 00477620306 R.E.A. UD-138461 ph. +39.0432.522970 fax +39.0432.522253 info@mmgrigliati.it




SCH 52/100_IFR

27.08.2018 - Rev. 5

MOLDED GRATINGS

Mesh	mm 52 x 52 main		
	mm 26 x 26 secondary		
Clear span	mm 19 x 19		
Height	mm 100		
Bearing bar	mm 10 upper part		
thickness	mm 8 bottom part		
Color	Grey RAL 7004 indicative RAL reference		



	Polyester Resin
Raw materials	Roving glass fiber type"E"
	Inorganic fillers without halogens

Resin type Modulus of elasticity		Ultimate stress	
IFR	15000 MPa	325 MPa	

Stand	dard panels	
mm	1010 x 1495	A FRENCE SE
		Stanne Stor
Weigh	nt kg/m² 56	
4.1	± mm 5 panel	
tolerance	dimensions ± mm 2 height	

	S	Smooth	Antiskid level R10 V10 norm DIN 51130
Surface	М	Meniscus	Antiskid level R13 V10 norm DIN 51130
	Α	Quartz	Antiskid level R13 V10 norm DIN 51130

Posstion to fire	Eiro rotordont	Spread ≤ 25 norm ASTM E84-98	
Reaction to fire Fire retardant	rife fetafuant	Level B _{ff} -S1 norm EN 13501-1	

Ageing resistance

Ageing test made with UV lamp according to ASTM G154-06 and passed with 5 points on the gray range and without evident defects (test made with 1500 hours of exposure to 4 hours alternate cycles at a UV temperature of 60°C and 4 hours at a condensed temperature of 50°C irradiated by UVB 313 nm lamp, radiance 0,71 W/m²)

After the exposure to heat, cold and humidity cycles according to UNI EN ISO 9142/04 norm (n° 21 cycles type D3) there is no evidence of defects



M.M. S.R.L. Fiberglass Reinforced Polymer gratings and structures

Via Antonio Zanussi, 300/302 33100 Udine - Italy Cap. Soc. EURO 100.000 i.v. P.Iva / C.F. 00477620306 Reg. Imp. UD 00477620306 R.E.A. UD-138461 ph. +39.0432.522970 fax +39.0432.522253 info@mmgrigliati.it



LOADS

MAXIMUM SUGGESTED LOADS

Limits determined by **Deflection** (load sagging)

the maximum deflection admitted, is 1/200 of the distance between the supports

According to the standard DIN 24537-3 deviation due to the load may be no more than 1/200 of the land width and the difference in height between neighbouring joints between loaded and unloaded floor coverings may be no more than 4 mm.

DISTRIBUTED LOAD			CONCENTRATED LOAD		
Distance between	Load with	Load with	Distance between	Load with	Load with
supports	deflection equal	deflection equal	supports	deflection equal	deflection equal
	to 1/200	to 1/100		to 1/200	to 1/100
[cm]	[kg	/m²]	[cm]	[Kg	ı/m]
80	18700	37400	80	9350	18700
100	9550	19150	100	5950	11950
120	5500	11050	120	4150	8300
140	3450	6950	140	3050	6100

All lighter loads are admitted

Limits determined by Admitted stresses (stress determined by the load)

the **maximum admitted stress** is 1/5 of the ultimate stress (safety factor is equal to 0.20 – the ultimate stress is 5 times the specified load)

DISTRIBUTED LOAD		CONCENTRATED LOAD	
Distance between supports	Maximum admitted load	Distance between supports	Maximum admitted load
[cm]	[kg/m²]	[cm]	[kg/m]
80	24750	80	9900
100	15800	100	7900
120	11000	120	6600
140	8050	140	5650

- The above characteristics are meant as reference values for standard material in ambient working temperature. Even if they are not to be considered as guaranteed characteristics they are based on our experience and are supplied in good faith.
- According to the standard DIN 24537-3 the conversion safety factor should be 0.75 for internal environmental exposure conditions, 0.65 for external exposure conditions, and 0.50 for aggressive exposure conditions.
- No matter which are the exposure conditions, chemical resistance must be always verified by contacting M.M.technical department.
- In case of heavy duty load compressive strength must be verified.