


**SCH 52/40\_ISO**


06.05.2011 - Rev. 4

**MOLDED GRATINGS**

<b>Mesh</b>	mm <b>52 x 52</b> main	
	mm <b>26 x 26</b> secondary	
<b>Clear span</b>	mm <b>19 x 19</b>	
<b>Height</b>	mm <b>40</b>	
<b>Bearing bar thickness</b>	mm <b>7</b> upper part	
	mm <b>5</b> bottom part	
<b>Color</b>	<b>Translucent green</b>	

<b>Raw materials</b>	<b>ISOPHTHALIC Polyester Resin</b>
	<b>Roving glass fiber type "E"</b>
	<b>Without inorganic fillers</b>

<b>Resin type</b>	<b>Modulus of elasticity</b>	<b>Ultimate stress</b>
<b>ISO</b>	12250 MPa	310 MPa

<b>Standard panels</b>	
mm 1000 x 2000	
mm 1000 x 3000	
mm 1000 x 4050	
mm 1500 x 2000	
<b>Weight kg/m²</b>	<b>19</b>
<b>tolerance</b>	± mm 5 panel dimensions
	± mm 2 height



<b>Surface</b>	S	<b>Smooth</b>	<b>Antiskid level R10 V10 norm DIN 51130</b>
	M	<b>Meniscus</b>	<b>Antiskid level R13 V10 norm DIN 51130</b>
	A	<b>Quartz</b>	<b>Antiskid level R13 V10 norm DIN 51130</b>

<b>Ageing resistance</b>	<b>Ageing test made with UV lamp according to ASTM G154-06 and passed with 5 points on the gray range and without evident defects</b> (test made with 1500 hours of exposure to 4 hours alternate cycles at a UV temperature of 60°C and 4 hours at a condensed temperature of 50°C irradiated by UVB 313 nm lamp, radiance 0,71 W/m²)
	<b>After the exposure to heat, cold and humidity cycles according to UNI EN ISO 9142/04 norm (n° 21 cycles type D3) there is no evidence of defects</b>



## LOADS

### MAXIMUM SUGGESTED LOADS

Type of support	On the line of the two ends of the panel
Limits determined by	<b>Deflection</b> (load sagging)
the <b>maximum deflection admitted</b> , is 1/200 of the distance between the supports	
According to the standard DIN 24537-3 deviation due to the load may be no more than 1/200 of the land width and the difference in height between neighbouring joints between loaded and unloaded floor coverings may be no more than 4 mm.	

DISTRIBUTED LOAD			CONCENTRATED LOAD			
	Distance between supports	Load with deflection equal to 1/200		Load with deflection equal to 1/100	Distance between supports	Load with deflection equal to 1/200
	[cm]	[kg/m <sup>2</sup> ]		[cm]	[kg/m]	
	50	3100	6200	50	950	1900
	70	1100	2250	70	450	950
	90	500	1050	90	300	600
	110	250	550	110	200	400
All lighter loads are admitted						

Limits determined by	<b>Admitted stresses</b> (stress determined by the load)
the <b>maximum admitted stress</b> is 1/5 of the ultimate stress (safety factor is equal to 0.20 – the ultimate stress is 5 times the specified load)	

DISTRIBUTED LOAD			CONCENTRATED LOAD		
	Distance between supports	Maximum admitted load		Distance between supports	Maximum admitted load
	[cm]	[kg/m <sup>2</sup> ]	[cm]	[kg/m]	
	50	6650	50	1650	
	70	3400	70	1150	
	90	2050	90	900	
	110	1350	110	750	
All lighter loads are admitted					

- The above characteristics are meant as reference values for standard material in ambient working temperature. Even if they are not to be considered as guaranteed characteristics they are based on our experience and are supplied in good faith.
- According to the standard DIN 24537-3 the conversion safety factor should be 0.75 for internal environmental exposure conditions, 0.65 for external exposure conditions, and 0.50 for aggressive exposure conditions.
- No matter which are the exposure conditions, chemical resistance must be always verified by contacting M.M.technical department.
- In case of heavy duty load compressive strength must be verified.