

M.M. S.R.L. Fiberglass Reinforced Polymer gratings and structures

Via Antonio Zanussi, 300/302 33100 Udine - Italy Cap. Soc. EURO 100.000 i.v. P.lva / C.F. 00477620306 Reg. Imp. UD 00477620306 R.E.A. UD-138461 ph. +39.0432.522970 fax +39.0432.522253 info@mmgrigliati.it




SCH 50/50C_IFR 06.05.2011 - Rev. 4

MOLDED GRATINGS

Mesh	mm 50 x 50	
Thickness	mm 53	
Cover thickness	mm 3	
Bearing bar	mm 8 upper part	
thickness	mm 5 bottom part	
Color	Grey RAL 7004 indicative RAL reference	

	Polyester Resin	
Raw materials	Roving glass fiber + Mat and Woven Fabric type"E"	
	Inorganic fillers without halogens	

Resin type	Modulus of elasticity	Ultimate stress
IFR	15000 MPa	250 MPa



Surface	А	Quartz		Antiskid level R13 V4 norm DIN 51130		
Reaction to fire Fire retardant				Spread ≤ 25 norm ASTM E84-98		
Reaction to fire	Fire retardant			Level B _{ff} -S1 norm EN 13501-1		
Ageing resistance	Ageing test made with UV lamp according to ASTM G154-06 and passed with 5 points on the gray range and without evident defects (test made with 1500 hours of exposure to 4 hours alternate cycles at a UV temperature of 60°C and 4 hours at a condensed temperature of 50°C irradiated by UVB 313 nm lamp, radiance 0,71 W/m²) After the exposure to heat, cold and humidity cycles according to UNI EN ISO 9142/04 norm (n° 21 cycles type D3) there is no evidence of defects					



Via Antonio Zanussi, 300/302 33100 Udine - Italy Cap. Soc. EURO 100.000 i.v. P.lva / C.F. 00477620306 Reg. Imp. UD 00477620306 R.E.A. UD-138461 ph. +39.0432.522970 fax +39.0432.522253 info@mmgrigliati.it



LOADS

MAXIMUM SUGGESTED LOADS

Type of support	On the line of the two ends of the panel	
Limits determined by	Deflection (load sagging)	

the **maximum deflection admitted**, is 1/200 of the distance between the supports According to the standard DIN 24537-3 deviation due to the load may be no more than 1/200 of the land width and the difference in height between neighbouring joints between loaded and unloaded floor coverings may be no more than 4 mm.

DISTRIBUTED LOAD	and the second s	
Distance between	Load with	Load with
supports	deflection equal	deflection equal
	to 1/200	to 1/100
[cm]	[kg/m ²]	
70	4900	9850
90	2300	4600
110	1250	2500
130	750	1500

Limits determined by

CONCENTRATED LOAD		
Distance between	Load with	Load with
supports	deflection equal to 1/200	deflection equal to 1/100
[cm] 70		4300
90	1300	2600
110	850	1700
130	600	1250

All lighter loads are admitted

Admitted stresses (stress determined by the load)

the **maximum admitted stress** is 1/5 of the ultimate stress (safety factor is equal to 0.20 – the ultimate stress is 5 times the specified load)

DISTRIBUTED LOAD	and the second s	CONCENTRATED LOAD	
Distance between supports	Maximum admitted load	Distance between supports	Maximum admitted load
[cm]	[kg/m ²]	[cm]	[kg/m]
70	7150	70	2500
90	4300	90	1950
110	2900	110	1600
130	2050	130	1350

All lighter loads are admitted

 The above characteristics are meant as reference values for standard material in ambient working temperature. Even if they are not to be considered as guaranteed characteristics they are based on our experience and are supplied in good faith.

According to the standard DIN 24537-3 the conversion safety factor should be 0.75 for internal environmental exposure conditions, 0.65 for external exposure conditions, and 0.50 for aggressive exposure conditions.

- No matter which are the exposure conditions, chemical resistance must be always verified by contacting M.M.technical department.

- In case of heavy duty load compressive strength must be verified.