



PULTRUDED PROFILES

Profile type "O" (53O2619)

Diameter 1	mm 25.4	
Diameter 2	mm 19	
Thickness 1	mm 3.2	
Thickness 2	mm -	
Standard Color	Grey RAL 7035 Yellow RAL 1018	
Standard Length	mm 6000 (± mm 10)	

J_x (mm ⁴)	J_y (mm ⁴)	Area (mm ²)	Weight (kg/m)
16034	16034	247	0,60

Fiberglass content (%)	60	ASTM D 792 / UNI 7092	Fiberglass content (%)	1.5	ASTM D638 / UNI 5819
Water absorption (%)	0.4	ISO 1172	Water absorption (%)	350	ASTM D790 / UNI 7219
Barcol hardness	50	ASTM 2583	Barcol hardness	14000	ASTM D790 / UNI 7219
Impact strength (Charpy) (kJ/m²)	180	ASTM D 256 / UNI 6062	Impact strength (Charpy) (kJ/m²)	-	-
Tensile strength (MPa)	400	ASTM D638 / UNI 5819	Tensile strength (MPa)	220	ASTM D695 / UNI 4279
Tensile modulus (MPa)	26000	ASTM D638 / UNI 5819	Tensile modulus (MPa)	20000	ASTM D695 / UNI 4279

Tolerances on the above values ± 10 % - UV protection on the surface – dimension tolerances according to ASTM D3917 norm – Surface according to ASTM D 2563 norm level II RAL reference is indicative.

The information specified in the above table is to be considered as an average value referred to tests carried out accordingly to the glass fiber direction (longitudinal direction) and are meant as reference values for standard material. Even if they are not to be considered as guaranteed characteristics they are based on our experience and are supplied in good faith.

Raw materials	Isophthalic polyester resin
	Roving glass fiber type "E" – Continuous strand mat – Polyester surface veil
For other colors, resins or reinforcements contact M.M. S.r.l. directly	

Ageing resistance	Ageing test made with UV lamp according to ASTM G154-06 and passed with 5 points on the gray range and without evident defects (test made with 1500 hours of exposure to 4 hours alternate cycles at a UV temperature of 60°C and 4 hours at a condensed temperature of 50°C irradiated by UVB 313 nm lamp, radiance 0,71 W/m ²)
	After the exposure to heat, cold and humidity cycles according to UNI EN ISO 9142/04 norm (n° 21 cycles type D3) there are no evidence of defects



MM S.r.l.

Via A. Zanussi 300 / 302, 33100 Udine (Italy)

Ph. +39 0432.602218 / 522970 - Fax. +39 0432.522253

info@mmgrigliati.it - www.mmgrigliati.it

53O2619I

27.10.2010

Rev. 2

COMPANY
WITH QUALITY MANAGEMENT
SYSTEM CERTIFIED BY DNV
ISO 9001:2000